

ISSN No: 2348-4845 International Journal & Magazine of Engineering, Technology, Management and Research

A Peer Reviewed Open Access International Journal

Tentative Evaluation of Nano Composite Concrete

M.Sarika Assistant Professor.

Department of Civil Engineering, Ramachandra College of Engineering.

ABSTRACT:

The development of construction materials technology, particularly concrete is growing very rapidly in the pres- ence of nanotechnology. Nanotechnology is the science of engineering that deals with the particle which are less than 100 nm in size. Hence here Nano silica is used as an additive to fill up the deviation, and it is possible because the silica(S) in the sand reacts with calcium hydrate in (CH) the cement at Nano scale to form C-S-H bond and it improves the strengthening factor of concrete. In this pa- per an attempt has been made to carry out an experimental investigation on concrete by replacing cement with 30%, 40% and 50% fly ash and an additive of 3% nano silica. The compressive strength, split tensile strength and flexural strength of concrete is found and is compared with Portland Pozzolana Cement (PPC).

INTRODUCTION:

Concrete technology is a multidisciplinary area of research where nanotechnology potentially offers the opportunity to improve the properties of concrete to suit the specific requirements. Addition of nano materials to concrete can lead to significant improvements in the strength and life of concrete. Nanotechnology is the science of engineer- ing that deals with particle which are less than 100 nm in size. The development of construction materials technology, particularly concrete is growing very rapidly in the presence of nanotechnology. Nano technology applied to concrete includes the use of nano materials like nano silica, nano fibers, etc. By adding nano materials, concrete composites with su- perior properties can be produced. Ordinary Portland ce- ment (OPC) is the main ingredient of concrete but the production of OPC releases about 5-7% of carbon dioxide into atmosphere hence there is a need to reduce the use of OPC in concrete. The use of flyash as partial replacement of cement is well researched and is widely used. The use of flyash is limited to a maximum of 25 to 30% by weight as a partial replacement of cement. Although the use of flyash is limited the high volume fly- ash is studied where the properties are inferior compared to the low volume flyash hence there is a deviation in strength of concrete. In order to overcome the deviation Nano silica is used as an additive.

EXPERIMENTAL INVESTIGATION:

The various materials used for the experimental investi- gation and various tests carried out are presented in this chapter.

FLYASH:

Fly ash is most commonly used as a pozzolan in PCC applications. Cement is the most costly and energyinten- sive component of concrete. The unit cost of concrete can be reduced by partial replacement of cement with fly ash. As per ASTM C 618 – 1993[17] there are two classes of fly ash namely class F and class C. Class F fly ash is pro- duced from burning anthracite or bituminous coal and is pozzolanic in nature and class C is obtained from lignite or subbituminous coal. Class C fly ash possesses both pozzolanic and self-hardening property. Hence, it is necessary to characterize the material scien- tifically to utilize it in different applications. The main chemical compounds of class F fly ash are silica, alumina and iron oxide.



ISSN No: 2348-4845 International Journal & Magazine of Engineering, Technology, Management and Research

A Peer Reviewed Open Access International Journal

Other minor constituents include oxides of calcium, magnesium, titanium, sulphur, sodium and potassium. Class C fly ash contains relatively higher pro- portion of calcium oxide and lesser proportion of silica, alumina and iron oxide than class F fly ash. The pozzolanic effect is the main effect of Fly ash, which states that the unfixed SiO2 and Al2O3 in FA can be ac- tivated by Ca (OH) 2 product of cement hydration and produce more hydrated gel. Since the gel produced from pozzolanic action can fill in the capillary in concrete.

S.No	properties	Values in
1	Si0 ₂	35.4
2	Al ₂ 0 ₃	17.5
3	Fe ₂ 0 ₃	5.3
4	ea0	26.1
5	Mg0	4.6
6	S03	2.8

NANO SILICA:

Nano silica is one of the silica fines with high potential as cement replacement and as concrete additive. There are different methods to produce nS products. One production method is based on Sol-gel process organic or water route at room temperature. In this process, the starting materi- als like Na2Sio4 and organo metallic's like TMOS/TEOS are added in a solvent and then the pH of the solution is changed reaching the precipitation of silica gel. The pro- duced gel is mixed and filtered to become a Xerogel. This is further dried and burned or dispersed again with stabi- lized agent (Na, K and NH3) to produce a concentrated dispersion with 20 to 40 % solid content suitable for use in concrete. There are other methods like vaporization of silica between 1500 to 2000 °C reducing quartz in an elec- tric arc furnace, biological method, precipitation method etc. Nano-Silica could significantly increase the compressive strength of concretes containing large fly ash volume at early age, by filling the pores between large fly ash and cement particles. Nano-silica decreases the setting time of mortar when compared with silica fume micro silica and reduces bleeding water and segregation by the improve- ment of the cohesiveness.

Concrete is a macro-material strongly influenced by its nano-properties. The addition of nano-silica (SiO2) to cement based ma- terials can control the degradation of the calcium-silicate hydrate reaction caused by calcium leaching in water, blocking water penetration and leading to improvements in durability. Nano silica can improve the performance of cement-based materials matrix through increased produc- tion of CSH gel due to pozzolanic reaction and reduced amount of Ca (OH)2 Nano Silica used in this project is brought from Ambattur industrial estate. Below Figure shows Nano Flyash and Nano Silica.



MIX DESIGN:

Mix	Cem	Water	Fine	Coarse	Fly ash
proportioning	ent	(kg)	aggregat	aggregate	(kg)
	(Kg)		e (kg)	(kg)	
per m ³					118.29
	276.	197.72	698.49	1132.80	
per bag of					
cement					
	50	22.5	92.57	138.5	15
Ratio	1	0.45	1.85	2.77	0.30

RESULTS AND DISCUSSION:


The compressive strength of 150x150x150 mm cubes of M25 grade concrete with 0%, 30%, 40% and 50% of ce- ment replaced with flyash and the same percentage of fly- ash replacement on an addition of 3% Nano Silica for 7 and 28 days respectively. It can be seen that the strength of concrete is reduced when the percentage of fly ash is increased. However there is an improvement in strength after adding nano silica. The percentage increase in com- pressive strength for 30%,40% and 50% cement replaced flyash concrete on addition of Nano silica of 3% after 28 days is 19%,21% and 13% to that of flyash replaced concrete.

Volume No: 4 (2017), Issue No: 5 (May) www.ijmetmr.com




ISSN No: 2348-4845 International Journal & Magazine of Engineering, Technology, Management and Research


A Peer Reviewed Open Access International Journal



Compressive strength comparison for 28 days



Split tensile strength comparison for 28 days



Flexural strength comparison for 28 days

CONCLUSION:

From the experimental work the following conclusions are drawn

» The strength of concrete is reduced when the percent- age of fly ash is increased. However there is an improve- ment in strength after adding nano silica.

» The percentage increase in compressive strength for 30%,40% and 50% cement replaced flyash concrete on addition of Nano silica of 3% after 28 days is 19%,21% and 13% to that of flyash replaced concrete.

» The percentage increase in Flexural strength for 30%,40% and 50% cement replaced flyash concrete on addition of Nano silica of 3% after 28 days is 32%,30% and 21% to that of the flyash replaced concrete.

» The percentage increase in Split tensile strength for 30%,40% and 50% cement replaced flyash concrete on addition of Nano silica of 3% after 28 days is 18%,16% and 15% to that of the flyash replaced concrete.

» The use of fly ash in concrete reduces the cement con- tent thereby reduction in carbon dioxide emission and be- comes green concrete.

REFERENCES:

1. perumalsamy Balaguru and Ken ehong, "Nanotechnology and concrete: Research opportunities" proceedings of AeI Session on "Nanotechnology of eoncrete: Re- cent Developments and Future perspectives" November 7, 2006, Denver, USA.

2. Zhi Ge and Zhili Gao, "Applications of Nanotechnol- ogy and Nano materials in eonstruction", First Interna- tional Conference on Construction In Developing Coun- tries (ICCIDC-I) Advancing and Integrating Construction Education, Research & Practice, August 4-5, 2008, Ka- rachi, pakistan.

3. Ozlem eelik, Erdem damsi and Sabriye piskin "Charac- terization of flyash and it effects on compressive strength properties of portland cement" Indian journal of engi- neering and material sciences. Vol 15October 2008 pp 433-440.

4. Babu Rao, J., p. Narayanaswami and K. Siva prasad, "Thermal stability of nano structured fly ash synthesized by high energy ball milling" International Journal of En- gineering, Science and Technology Vol. 2, No. 5, 2010.

Volume No: 4 (2017), Issue No: 5 (May) www.ijmetmr.com

May 2017